

30 Colours / **1** Finish / **2** Sizes

From trend-setting grey wood, through contemporary mid tones to more traditional dark wood and a vast array of stone effects, the diversity of LX Hausys Decotile 30 makes it the perfect choice for a variety of installations.









Floor: EVLX 158-30 Matt



Sizes: Wood-Effect

1			
Size (mm)	Thickness	Finish	Colour Availability

1	Dryback	2	Matt	EVLX 101-30 to 122-30
	180 x 1200			

Swatch colours may vary from original. Samples should be requested.

Specification

Format:	Plank
Treatment:	PUR
Edge Detail:	Square-edged (no bevel)
Sustainability:	100% phthalate-free. Low VOC.
Durability:	Class 23 Domestic
	Class 31 Commercial
Application:	Internal use only. Suitable with underfloor heating
Installation:	Recommended for bonded installation
Wear Layer:	0.3mm
Residential Warranty:	25 years
Commercial Warranty:	7 years

EVLX 117-30

DOMUS





EVLX 151-30

EVLX 157-30

EVLX 152-30



EVLX 154-30



EVLX 155-30



EVLX 156-30



```
EVLX 158-30
```

Sizes: Stone-Effect



	Size (mm)	Thickness	Finish	Colour Availability
1	Dryback 300 x 600	2	Matt	EVLX 151-30 to 158-30

Swatch colours may vary from original. Samples should be requested.

Specification

Format:	Tile
Treatment:	PUR
Edge Detail:	Square-edged (no bevel)
Sustainability:	100% phthalate-free. Low VOC.
Durability:	Class 23 Domestic
	Class 31 Commercial
Application:	Internal use only. Suitable with underfloor heating
Installation:	Recommended for bonded installation
Wear Layer:	0.3mm
Residential Warranty:	25 years
Commercial Warranty:	7 years

LX Hausys Decotile 30

Technical Data

Technical Data

Engineered Vinyl

PERFORMANCE & DURABILITY

Technical Characteristics	Industry Standard	Performance	
Type of Flooring	EN ISO 10582	PVC Heterogeneous	
Straightness & Squareness	EN ISO 24342	≤ 0.15% / ≤ 0.35mm	
Classification	EN ISO 10874	Class 23/31	
Weight	EN ISO 23997	3.9kg/sqm	
Wear Resistance	EN 660-2	Т	
Residual Indentation	EN ISO 24343-1	≤ 0.1mm	
Dimensional Stability	EN ISO 23999	< 0.10%	
Curling	EN ISO 23999	≤ 2mm	
Light Fastness	EN ISO 105-B02	≥ 6	
Furniture Leg Resistance	EN ISO 16581	No Crack, No Damage	
Castor Chair Resistance	EN ISO 4918	No Change	
Reaction to Fire	EN 13501-1	Bfl-s1	

NB: Compatible with underfloor heating systems - subject to K21 installation advice available on request.

All test results are based upon current test data provided by the manufacturer and are provided in good faith. Domus Group Limited cannot be held responsible for any variation in the test data due to changes in manufacture or material characteristics. Warranty is valid only when installed in accordance with LX Hausys Installation & Maintenance guide. Errors & omissions excepted. Please refer to Domus Group Limited Terms & Conditions of Sale, March 2024.



PERFORMANCE & DURABILITY

Technical Characteristics	Industry Standard	Performance
Stain Resistance	EN ISO 26987	No Change PUR Surface Treatment
Slip Resistance	BS EN ISO 10545-17 (DIN 51130)	R10 (from 10° to 19°)
Acoustic Insulation	EN ISO 717-2	3dB
Electrostatic Performance	EN 1815	< 2kV
Thermal Resistance	EN ISO 12667	0.0042m².K/W
Underfloor Heating		Suitable Max. 29.4°C 85°F
Formaldehyde Group	EN 14041:2004/AC:2006	E1
CE Marking	EN 14041:2004/AC:2006	DOP N° 19EDB-DOP-03
TVOC After 28 Days	ISO 16000	A+ (Eurofins 392-201800200803_E_EN)
REACH	N° SVHC	SGS AYAA18-62889

NB: Compatible with underfloor heating systems - subject to K21 installation advice available on request.

All test results are based upon current test data provided by the manufacturer and are provided in good faith. Domus Group Limited cannot be held responsible for any variation in the test data due to changes in manufacture or material characteristics. Warranty is valid only when installed in accordance with LX Hausys Installation & Maintenance guide. Errors & omissions excepted. Please refer to Domus Group Limited Terms & Conditions of Sale, March 2024.