# **Eccentric Luxe**

Porcelain Marble



## 6 Colours / 2 Finishes / 2 Sizes

Inspired by the grandeur of exclusive settings, Eccentric Luxe captures the captivating beauty and inherent luxury of onyx. This porcelain tile range is based on a virtuous, sustainable approach and is part of Florim's 'CarbonZero' selection of Climate-Positive surfaces, which reduce the amount of  ${\rm CO_2}$  in the atmosphere.





Wall & Floor: DREX 01 Glossy



Wall: DREX 01 Glossy

DREX 04

DREX 03

DREX 01



DREX 02 DREX 05



Sizes

_	
1	
'	
	2
	1 1 2

	Size (mm)	Thickness	Finish	Colour Availability
1	1797 x 797 (R)	9	Glossy	All colours
2	1197 x 597 (R)	9	Comfort PTV Glossy	All colours All colours
	Plinth Skirting 1197 x 46	9	Glossy	All colours
	Bullnose Step Tread 1197 x 33	30	Glossy	All colours

<sup>(</sup>R) Rectified size – square edge with bevel. Swatch colours may vary from original. Samples should be requested.





# **V4 - Random Shade Variation**

# **V2 - Moderate Shade Variation**




DREX 03 Comfort PTV



DREX 04 Glossy




DREX 05 Comfort PTV



DREX 06 Glossy



DREX 01 Comfort PTV



DREX 02 Glossy

## **Eccentric Luxe**

Technical Data

Product Type: Unglazed Porcelain (BS EN 14411 - Group Bla)

Use: Floors & Walls Product Code: DREX

### **DIMENSION & SURFACE QUALITY**

Technical Characteristics	Industry Standards	Requirement	Actual Value
Length & width	BS EN ISO 10545-2	± 0.60% (max. ± 2.0mm)	Conforms
Thickness	BS EN ISO 10545-2	± 5% (max. ± 0.5mm)	Conforms
Edge straightness	BS EN ISO 10545-2	± 0.50% (max. ± 1.5mm)	Conforms
Orthogonality (squareness)	BS EN ISO 10545-2	± 0.50% (max. ± 2.0mm)	Conforms
Planarity (flatness)	BS EN ISO 10545-2	± 0.50% (max. ± 2.0mm)	Conforms
Appearance	BS EN ISO 10545-2	> 95%	Conforms

#### SLIP RESISTANCE

Technical Characteristics	Industry Standards	Requirement	Finish
Areas with footwear	BS EN 16165 Annex B	R10 from 10° to 19°	Comfort PTV
Areas with bare feet	BS EN 16165 Annex A	B over 18° to 24°	Comfort PTV
Slip resistance (Pendulum) Coefficient of friction	BS EN 16165 Annex C	Test results upon request	

### PRODUCT QUALITY & DURABILITY

Technical Characteristics	Industry Standards	Requirement	Actual Value
Water absorption	BS EN ISO 10545-3	≤ 0.5%	0.08% (Average Value)
Modulus of rupture (bending strength)	BS EN ISO 10545-4	≥ 35 N/mm²	50 N/mm² (Average Value)
Breaking strength	BS EN ISO 10545-4	≥ 7.5mm ≥ 1300 N	2200 N (Average Value)
Resistance to deep abrasion (unglazed tiles)	BS EN ISO 10545-6	≤175 mm³	140 mm³ (Average Value)
Thermal shock resistance	BS EN ISO 10545-9	No visible defects	Resistant
Frost resistance	BS EN ISO 10545-12	No surface alteration	Resistant
Chemical resistance: Low concentrations of acids & alkalis	BS EN ISO 10545-13	No visible defects	ULA – Comfort PTV ULB – Glossy
High concentrations of acids & alkalis	BS EN ISO 10545-13	No visible defects	UHA – Comfort PTV UHB – Glossy
Domestic chemicals & additives for swimming pools	BS EN ISO 10545-13	UB/GB min.	UA
Stain resistance	BS EN ISO 10545-14	Declared value - unglazed	Class 4
Reaction to fire	Based on the decision 96/603/EC and its changes	A1 <sub>FL</sub> /A1	A1 <sub>FL</sub> /A1
Recycled content			22.5%















