Tape

Porcelain Design

Wall: DTPE 01 Cobble,
DTPE 05 Cobble & DTPE 05 Cobble Half Glazed

5 Colours / **1** Finish / **9** Patterns / **1** Size

A Porcelain Design range consisting of colourful patterns overlaid onto two base tiles, that create soft, fabric-like effects. The different colours and patterns are designed to blend and be paired.

Design Raw Edges

MUTINA

Floor: DTPE 01 Base, Mesh & Mesh Half,
DTPE 04 Cobble, Cobble Half, Zigzag & Zigzag Half Glazed

Floor: DTPE 02 Mesh, Mesh Half, Cobble & Cobble Half Glazed

Wall: DTPE 01 Base, DTPE 03 Zigzag, Zigzag Half, Mesh, Mesh Half, Grainy & Grainy Half Glazed
Floor: DTPE 03 Grainy & Zigzag Glazed

DTPE 01 Base

DTPE 05 Base

Sizes



	Size (mm)	Thickness	Pattern	Colour Availability
1	205 x 205 (N)	10	Base	DTPE 01 & 05
			Mesh Mesh Half Cobble Cobble Half Grainy Grainy Half Zigzag Zigzag Half	All colours

(N) Nominal size – pressed edge. Nine different surface patterns in a Glazed finish. Swatch colours may vary from original. Tile samples should be requested.

V1 – Low
Shade Variation

DOMUS

service@domusgroup.com | t: 020 8481 9500 | domusgroup.com

Tape

Technical Data

Product Type: Glazed Porcelain (BS EN 14411 – Group BIa)

Use: Floors & Walls

Product Code: DTPE

DIMENSION & SURFACE QUALITY

Technical Characteristics	Industry Standards	Requirement	Actual Value
Length & width	BS EN ISO 10545-2	± 0.60% (max. ± 2.0mm)	Conforms
Thickness	BS EN ISO 10545-2	± 5% (max. ± 0.5mm)	Conforms
Edge straightness	BS EN ISO 10545-2	± 0.50% (max. ± 1.5mm)	Conforms
Orthogonality (squareness)	BS EN ISO 10545-2	± 0.50% (max. ± 2.0mm)	Conforms
Planarity (flatness)	BS EN ISO 10545-2	± 0.50% (max. ± 2.0mm)	Conforms
Appearance	BS EN ISO 10545-2	> 95%	Conforms

SLIP RESISTANCE

Technical Characteristics	Industry Standards	Requirement	Finish
Areas with footwear	BS EN ISO 10545-17 (DIN 51130)	R10 from 10° to 19°	Glazed
Slip resistance Coefficient of friction	BS 7976-2	Test results upon request	

PRODUCT QUALITY & DURABILITY

Technical Characteristics	Industry Standards	Requirement	Actual Value
Water absorption	BS EN ISO 10545-3	≤ 0.5%	0.06% (typical value)
Modulus of rupture (bending strength)	BS EN ISO 10545-4	≥ 35 N/mm2	Conforms
Breaking strength	BS EN ISO 10545-4	≥ 1300 N	Conforms
Resistance to surface abrasion	BS EN ISO 10545-7	PEI* see classifications below	DTPE 05 – Class 3 DTPE 01, 02, 03 & 04 – Class 4
Thermal shock resistance	BS EN ISO 10545-9	No visible defects	Resistant
Crazing resistance	BS EN ISO 10545-11	No visible signs	Resistant
Frost resistance	BS EN ISO 10545-12	No surface alteration	Resistant
Chemical resistance: Low concentrations of acids & alkalis	BS EN ISO 10545-13	No visible defects	GLA-GLB
High concentrations of acids & alkalis	BS EN ISO 10545-13	No visible defects	GHA-GHB
Domestic chemicals & additives for swimming pools	BS EN ISO 10545-13	GB min.	A
Stain resistance	BS EN ISO 10545-14	Min. Class 3	Class 5
Reaction to fire	Based on the decision 96/603/EC and its changes	$A1/A1_{FL}$	$A1/A1_{FL}$
Recycled content			20%

***PEI classifications**
PEI 2 - Light traffic
PEI 3 - Light to moderate traffic
PEI 4 - Moderate to heavy traffic
PEI 5 - Heavy to extra heavy traffic

Recycled Content

ENVIRONMENTAL PRODUCT DECLARATION EPD ISO 14025:2010 CERTIFIED

All test results are based upon current test data provided by the manufacturer and are provided in good faith. Domus Group cannot be held responsible for any variation in the test data due to changes in manufacture or material characteristics. Errors & omissions excepted. Please refer to Domus Group Terms & Conditions of Sale.

October 2019

DOMUS

service@domusgroup.com | t: 020 8481 9500 | domusgroup.com