

Glace

### 6 Colours / 1 Finish / 2 Sizes

Glace is a range of porcelain tiles in natural colours and a three-dimensional structure available in every shade. Along the sides of the tiles and in parts of their surfaces, there are touches of a clay colour that give the impression of gaps in the glaze, a distinctive feature of the handmade materials that inspire this range.







Wall: DMRG 02 Glossy

Wall: DMRG 03 3D Glossy





DMRG 02







DMRG 04



DMRG 05


DMRG 04 3D




DMRG 05 3D



200mm



DMRG 06 3D




DMRG 03




DMRG 03 3D





	Size (mm)	Thickness	Finish	Colour Availability
1	200 x 75 (N)	9	Glossy	All colours
2	3D 200 x 75 (N)	11.5	Glossy	All colours

(N) Nominal size - pressed edge. Swatch colours may vary from original. Samples should be requested.






# V2 - Moderate Shade Variation






DMRG 01

DMRG 02











DMRG 06





DMRG 01 3D

DMRG 02 3D






DMRG 03 3D



DMRG 05 3D

DMRG 04 3D



DMRG 06 3D

## Glace

Technical Data

Product Type: Glazed Porcelain (BS EN 14411 – Group Bla) Use: Walls (Internal & External) Product Code: DMRG

### **DIMENSION & SURFACE QUALITY**

Technical Characteristics	Industry Standards	Requirement (for 70mm ≤N<150mm		Actual Value
Length & width	BS EN ISO 10545-2	± 0.9mm	± 0.60% (max. ± 2.0mm)	Conforms
Thickness	BS EN ISO 10545-2	± 0.5mm	± 5% (max. ± 0.5mm)	Conforms
Edge straightness	BS EN ISO 10545-2	± 0.75mm	± 0.50% (max. ± 1.5mm)	Conforms
Orthogonality (squareness)	BS EN ISO 10545-2	± 0.75mm	± 0.50% (max. ± 2.0mm)	Conforms
Planarity (flatness)	BS EN ISO 10545-2	± 0.75mm	± 0.50% (max. ± 2.0mm)	Conforms
Appearance	BS EN ISO 10545-2	> 95%		Conforms

### PRODUCT QUALITY & DURABILITY

Technical Characteristics	Industry Standards	Requirement	Actual Value
Water absorption	BS EN ISO 10545-3	≤ 0.5%	Conforms
Modulus of rupture (bending strength)	BS EN ISO 10545-4	$\geq$ 35 N/mm <sup>2</sup>	Conforms
Breaking strength	BS EN ISO 10545-4	≥7.5mm ≥1300 N	Conforms
Linear thermal expansion coefficient	BS EN ISO 10545-8	Declared value	Conforms
Thermal shock resistance	BS EN ISO 10545-9	No visible defects	Resistant
Crazing resistance	BS EN ISO 10545-11	No visible signs	Resistant
Frost resistance	BS EN ISO 10545-12	No surface alteration	Resistant
Chemical resistance: Low concentrations of acids & alkalis High concentrations of acids & alkalis	BS EN ISO 10545-13 BS EN ISO 10545-13	No visible defects No visible defects	GLA-GLB GHA-GHB
Domestic chemicals & additives for swimming pools	BS EN ISO 10545-13	UB/GB min.	GA
Stain resistance	BS EN ISO 10545-14	Min. Class 3 - glazed	Class 5
Reaction to fire	Based on the decision 96/603/EC and its changes	A1	A1
Recycled content			23%



All test results are based upon current test data provided by the manufacturer and are provided in good faith. Domus Group cannot be held responsible for any variation in the test data due to changes in manufacture or material characteristics. Errors & omissions excepted. Please refer to Domus Group Terms & Conditions of Sale. November 2023