

Kendo Slab

Fabricated Slabs / Porcelain Stone



DLKNX 01 Soft Textured

2 Colours / 2 Finishes / 1 Size

Kendo Slab draws inspiration from the protected stone of the Bavarian Jura Mountains, formed from marine deposits. This fabricated porcelain slab range depicts dark-coloured organic-shaped markings with an extraordinary richness of intensities.



DLKNX 02 Honed

Sizes



DLKNX 01



DLKNX 02



	Size (mm)	Thickness	Finish	Colour Availability
1	3240 x 1600	12	Honed	All colours
			Soft Textured	All colours

Swatch colours may vary from original. Samples should be requested.

Kendo Slab

Technical Data

Product Type: Glazed Porcelain (BS EN 14411 – Group BIa)

DIMENSION & SURFACE QUALITY

Technical Characteristics	Industry Standards	Requirement	Actual Value
Length & width	BS EN ISO 10545-2	± 0.60% (max. ± 2.0mm)	Conforms
Thickness	BS EN ISO 10545-2	± 5% (max. ± 0.5mm)	Conforms
Planarity (flatness)	BS EN ISO 10545-2	± 0.50% (max. ± 2.0mm)	Conforms

PRODUCT QUALITY & DURABILITY

Technical Characteristics	Industry Standards	Requirement	Actual Value
Water absorption	BS EN ISO 10545-3	≤ 0.5%	0.1% (Typical Value)
Impact Resistance	BS EN ISO 10545-5	Declared value	≥ 0.80 (Typical Value)
Linear thermal expansion coefficient	BS EN ISO 10545-8	Declared value	≤ 7 x 10 ⁻⁶ / °C ⁻¹ (Typical Value)
Thermal shock resistance	BS EN ISO 10545-9	No visible defects	Resistant
Frost resistance	BS EN ISO 10545-12	No surface alteration	Resistant
Chemical resistance: Low concentrations of acids & alkalis	BS EN ISO 10545-13	No visible defects	GLA
High concentrations of acids & alkalis	BS EN ISO 10545-13	No visible defects	GHA
Domestic chemicals & additives for swimming pools	BS EN ISO 10545-13	B min.	GA
Stain resistance	BS EN ISO 10545-14	Min. Class 3 – glazed	Class 5
UV Resistance	DIN 51094	No visible defects	Conforms
Reaction to fire	Based on the decision 96/603/EC and its changes	A1 _{FL} /A1	A1 _{FL} /A1

All test results are based upon current test data provided by the manufacturer and are provided in good faith. Domus Group cannot be held responsible for any variation in the test data due to changes in manufacture or material characteristics. Errors & omissions excepted. Please refer to Domus Group Terms & Conditions of Sale.

DOMUS

fabrication@domusgroup.com | t: 020 8481 9500 | domusgroup.com