

Maté

Porcelain Concrete



4 Colours / 1 Finish / 6 Sizes / 1 Mosaic

Maté draws inspiration from clay, the primordial building material shaped by time and human hands. This range encompasses four distinct colours and a variety of sizes, featuring hexagonal and chevron designs that form an expansive interpretive toolkit for reimagining contemporary spaces.



Floor: DFZT 04 Hexagon Natural



Floor: DFZT 03 Natural



Floor: DFZT 04 Chevron Natural




DFZT 02



DFZT 03



DFZT 05




DFZT 04

Hexagon




DFZT 02



DFZT 03




DFZT 04




DFZT 05

Sizes



	Size (mm)	Thickness	Finish	Colour Availability
1	595 x 595 (R)	9.5	Natural	All colours
2	595 x 296 (R)	9.5	Natural	All colours
3	595 x 73 (R)	9.5	Natural	All colours
4	Chevron 586.5 x 72 (R)	9.5	Natural	All colours
5	Hexagon 223 x 195 (R)	9.5	Natural	All colours
6	194 x 194 (R)	9.5	Natural	All colours

(R) Rectified size - square edge with bevel. A box of Chevron contains six pieces each of Chevron Right and Chevron Left mixed together. Swatch colours may vary from original. Samples should be requested. Mosaics and special pieces shown on next page.



Chevron



DFZT 02 Chevron



DFZT 03 Chevron



DFZT 04 Chevron



DFZT 05 Chevron


Mosaic




DFZT 02 Mosaic



DFZT 03 Mosaic




DFZT 04 Mosaic



DFZT 05 Mosaic


Mosaics & Special Pieces



Floor: DFZT 02 Chevron Natural

	Size (mm)	Thickness	Finish	Colour Availability
1	Mosaic 47 x 47 (R) on 296 x 296 sheet	9.5	Natural	All colours
	Skirting 595 x 73 (R)	9.5	Natural	All colours


(R) Rectified size - square edge with bevel. Swatch colours may vary from original. Samples should be requested.



DOMUS

service@domusgroup.com | t: 020 8481 9500 | domusgroup.com

V3 - High Shade Variation



DFZT 02



DFZT 03



DFZT 05



DFZT 04



DFZT 02 Hexagon

Maté

Technical Data

Product Type: Glazed Porcelain (BS EN 14411 – Group Bla)

Use: Floors & Walls

Product Code: DFZT

DIMENSION & SURFACE QUALITY

Technical Characteristics	Industry Standards	Requirement	Actual Value
Length & width	BS EN ISO 10545-2	± 0.60% (max. ± 2.0mm)	Conforms
Thickness	BS EN ISO 10545-2	± 5% (max. ± 0.5mm)	Conforms
Edge straightness	BS EN ISO 10545-2	± 0.50% (max. ± 1.5mm)	Conforms
Orthogonality (squareness)	BS EN ISO 10545-2	± 0.50% (max. ± 2.0mm)	Conforms
Planarity (flatness)	BS EN ISO 10545-2	± 0.50% (max. ± 2.0mm)	Conforms
Appearance	BS EN ISO 10545-2	> 95%	Conforms

SLIP RESISTANCE

Technical Characteristics	Industry Standards	Requirement	Finish
Areas with footwear	BS EN ISO 10545-17 (DIN 51130)	R9 from 3° to 10° R10 from 10° to 19°	DFZT 01 & 06 Natural DFZT 02, 03, 04 & 05 Natural
Slip resistance Coefficient of friction	BS 7976-2	Test results upon request	

PRODUCT QUALITY & DURABILITY

Technical Characteristics	Industry Standards	Requirement	Actual Value
Water absorption	BS EN ISO 10545-3	≤ 0.5%	0.3% (Typical value)
Modulus of rupture (bending strength)	BS EN ISO 10545-4	≥ 35 N/mm ²	42 N/mm ² (Typical value)
Resistance to surface abrasion (of glazed tiles)	BS EN ISO 10545-7	PEI *see classifications below	Class 5 – DFZT 01, 02 & 03 Class 4 – DFZT 04, 05 & 06
Thermal shock resistance	BS EN ISO 10545-9	No visible defects	Resistant
Crazing resistance	BS EN ISO 10545-11	No visible signs	Resistant
Frost resistance	BS EN ISO 10545-12	No surface alteration	Resistant
Chemical resistance: Low concentrations of acids & alkalis	BS EN ISO 10545-13	No visible defects	GLA
High concentrations of acids & alkalis	BS EN ISO 10545-13	No visible defects	GHA
Domestic chemicals & additives for swimming pools	BS EN ISO 10545-13	GB min.	GA
Stain resistance	BS EN ISO 10545-14	Min. Class 3	Class 5
Reaction to fire	Based on the decision 96/603/EC and its changes	A1 _{FL} /A1	A1 _{FL} /A1
Recycled content			10%

*PEI classifications

PEI 2 - Light traffic
PEI 3 - Light to moderate traffic
PEI 4 - Moderate to heavy traffic
PEI 5 - Heavy to extra heavy traffic



All test results are based upon current test data provided by the manufacturer and are provided in good faith. Domus Group cannot be held responsible for any variation in the test data due to changes in manufacture or material characteristics. Errors & omissions excepted. Please refer to Domus Group Terms & Conditions of Sale. June 2020

DOMUS

service@domusgroup.com | t: 020 8481 9500 | domusgroup.com