

# Koeda

*Ceramic Design*



Wall: DAKS 09 Mosaic Cracquele

**13 Colours / 2 Finishes / 1 Mosaic**

Koeda is a stunning range of double-fired, handmade ceramic mosaics. Crafted with natural glazes, they come in a captivating selection of vivid, artistic colours. Available in glossy and cracquele finishes, these mosaics are perfect for creating a unique and eye-catching statement in residential or commercial settings.



Wall: DAKS 10 Mosaic Cracquele





Wall: DAKS 12 Mosaic Cracquele



Wall: DAKS 13 Mosaic Cracquele

# Mosaics



DAKS 01 Mosaic



DAKS 03 Mosaic




DAKS 02 Mosaic




DAKS 04 Mosaic




DAKS 06 Mosaic




DAKS 09 Mosaic




DAKS 10 Mosaic




DAKS 11 Mosaic




DAKS 07 Mosaic




DAKS 13 Mosaic



DAKS 05 Mosaic



DAKS 12 Mosaic




DAKS 08 Mosaic

1


	Size (mm)	Thickness	Finish	Colour Availability
1	Mosaic 146 x 20 (N) on 295 x 292 sheet	9.5	Glossy Cracquele	DAKS 01, 02, 03, 04, 05, 06, 07 & 08 DAKS 09, 10, 11, 12 & 13

(N) Nominal size – pressed edge. Swatch colours may vary from original. Samples should be requested.  
Recommended for use on internal walls only.



# Koeda

Technical Data

Product Type: Glazed Ceramic (BS EN 14411 – Group BIII)

Use: Walls (Internal only)

Product Code: DAKS 01 – 08 (Glossy) & DAKS \*09-13 (Cracquele)

\* Note : Cracquele glazed tiles will require sealing with e.g. FILA MP90 Eco Xtreme prior to grouting

### DIMENSION & SURFACE QUALITY

Technical Characteristics	Industry Standards	Requirement (for nominal size <i>N</i> )		Actual Value
		70mm ≤N<150mm	N ≥ 150mm	
Length & width	BS EN ISO 10545-2	± 0.75mm	± 0.50% (max. ± 2.0mm)	Conforms
Thickness	BS EN ISO 10545-2	± 0.5mm	± 10% (max. ± 0.5mm)	Conforms

### PRODUCT QUALITY & DURABILITY

Technical Characteristics	Industry Standards	Requirement	Actual Value
Water absorption	BS EN ISO 10545-3	> 10%	Conforms
Modulus of rupture (bending strength)	BS EN ISO 10545-4	≥ 7.5mm thick ≥ 12 N/mm²	Conforms
Breaking strength	BS EN ISO 10545-4	≥ 7.5mm thick ≥ 600 N	Conforms
Thermal shock resistance	BS EN ISO 10545-9	No visible defects	Resistant (Glossy)
Crazing resistance	BS EN ISO 10545-11	No visible signs	Resistant (Glossy)
Chemical resistance: Low concentrations of acids & alkalis	BS EN ISO 10545-13	No visible defects	GLA (Glossy)
Domestic chemicals & additives for swimming pools	BS EN ISO 10545-13	GB min.	GA (Glossy)
Stain resistance	BS EN ISO 10545-14	Min. Class 3	Class 5 (Glossy)
Reaction to fire	Based on the decision 96/603/EC and its changes	A1	A1
Recycled content			38%



All test results are based upon current test data provided by the manufacturer and are provided in good faith. Domus Group cannot be held responsible for any variation in the test data due to changes in manufacture or material characteristics. Errors & omissions excepted. Please refer to Domus Group Terms & Conditions of Sale.  
May 2025