

Gleam 20mm

External 20mm / Porcelain Stone



4 Colours / 1 Finish / 1 Size

Gleam 20mm transforms Mediterranean light into a refined stone-effect porcelain inspired by Salento's natural beauty. Combine with Gleam's 9mm tiles to create a seamless flow between outdoor and indoor spaces. The durable 20mm thickness ensures strength, continuity and timeless style.





DXFCG 01



DXFCG 02



DXFCG 03




DXFCG 04

Sizes



	Size (mm)	Thickness	Finish	Colour Availability
1	1198 x 598 (R)	20	Bush Hammered	All colours

(R) Rectified size - square edge with bevel. Swatch colours may vary from original. Samples should be requested. Special pieces shown on next page. Recommended for outdoor use.






Floor: DXFCG 04 Bush Hammered

Special Pieces

	Size (mm)	Thickness	Finish	Colour Availability
1	Grill Component 598 x 150	9	Bush Hammered	All colours
2	Step Tread with Groove, Straight Edge & Drip Flop 598 x 300	9	Bush Hammered	All colours
3	Bullnose Step Tread 598 x 300	9	Bush Hammered	All colours
4	Bullnose Step Tread with Groove & Drip Flap 598 x 300	9	Bush Hammered	All colours

Swatch colours may vary from original. Samples should be requested.



V2 - Moderate
Shade Variation

DOMUS

service@domusgroup.com | t: 020 8481 9500 | domusgroup.com

Gleam 20mm

Technical Data

Product Code: DXFCG

DIMENSION & SURFACE QUALITY

Technical Characteristics	Industry Standards	Requirement	Actual Value
Length & width	BS EN ISO 10545-2	± 0.60% (max. ± 2.0mm)	Conforms
Thickness	BS EN ISO 10545-2	± 5% (max. ± 0.5mm)	Conforms
Edge straightness	BS EN ISO 10545-2	± 0.50% (max. ± 1.5mm)	Conforms
Orthogonality (squareness)	BS EN ISO 10545-2	± 0.50% (max. ± 2.0mm)	Conforms
Planarity (flatness)	BS EN ISO 10545-2	± 0.50% (max. ± 2.0mm)	Conforms

SLIP RESISTANCE

Technical Characteristics	Industry Standards	Requirement	Finish
Areas with footwear	BS EN 16165 Annex B	R11 from 19° to 27°	Bush Hammered
Areas with bare feet	BS EN 16165 Annex A	C over 24°	Bush Hammered
Slip resistance (Pendulum) Coefficient of friction	BS EN 16165	Test results upon request	

PRODUCT QUALITY & DURABILITY

Technical Characteristics	Industry Standards	Requirement	Actual Value
Water absorption	BS EN ISO 10545-3	≤ 0.5%	0.05% (Average value)
Modulus of rupture (bending strength)	BS EN ISO 10545-4	≥ 35 N/mm ²	50 N/mm ² (Average value)
Breaking strength	BS EN ISO 10545-4	≥ 7.5mm ≥ 1300 N	13600 N (Average value)
Resistance to deep abrasion (unglazed tiles)	BS EN ISO 10545-6	≤ 175 mm ³	145 mm ³ (Average value)
Linear thermal expansion coefficient	BS EN ISO 10545-8	Declared value	≤ 7 x 10 ⁻⁶ °C ⁻¹ (Average value)
Frost resistance	BS EN ISO 10545-12	No surface alteration	Resistant
Chemical resistance: Low concentrations of acids & alkalis	BS EN ISO 10545-13	No visible defects	ULA
High concentrations of acids & alkalis	BS EN ISO 10545-13	No visible defects	UHA
Stain resistance	BS EN ISO 10545-14	Declared value - unglazed	Class 5
Reaction to fire	Based on the decision 96/603/EC and its changes	A1 _{FL} /A1	A1 _{FL} /A1
Recycled content			≥ 40%



All test results are based upon current test data provided by the manufacturer and are provided in good faith. Domus Group cannot be held responsible for any variation in the test data due to changes in manufacture or material characteristics. Errors & omissions excepted. Please refer to Domus Group Terms & Conditions of Sale. April 2026

DOMUS

service@domusgroup.com | t: 020 8481 9500 | domusgroup.com