

Manifattura

Porcelain Design



Wall: DFMS 16 Tracce Décor Glazed

4 Colours / 1 Finish / 1 Size / 4 Décors

Manifattura redefines the porcelain tile experience with its vibrant, innovative approach. Inspired by the artistry of handmade ceramics, this range features deep, uneven glazes that create a unique, tactile surface. The interplay of light and shadow on these textured edges adds depth and character to each tile.



Wall: DFMS 11 Cerchi Décor Glazed



DFMS 01



DFMS 02




DFMS 04




DFMS 06

Sizes



	Size (mm)	Thickness	Finish	Colour Availability
1	200 x 200 (N)	8.5	Glazed	All colours

(N) Nominal size – pressed edge. Swatch colours may vary from original. Samples should be requested. Décors shown on next page.



Décors



DFMS 11 Cerchi Décor





DFMS 12 Sagome Décor



DFMS 14 Combinazioni Décor



DFMS 16 Tracce Décor



	Size (mm)	Thickness	Finish	Colour Availability
1	Cerchi Décor 200 x 200 (N)	8.5	Glazed	DFMS 11
	Sagome Décor 200 x 200 (N)	8.5	Glazed	DFMS 12
	Combinazioni Décor 200 x 200 (N)	8.5	Glazed	DFMS 14
	Tracce Décor 200 x 200 (N)	8.5	Glazed	DFMS 16

(N) Nominal size - pressed edge. Swatch colours may vary from original. Samples should be requested.

V2 - Moderate
Shade Variation

DOMUS

service@domusgroup.com | t: 020 8481 9500 | domusgroup.com

Manifattura

Technical Data

Product Type: Glazed Porcelain (BS EN 14411 – Group BIa)

Use: Walls

Product Code: DFMS

DIMENSION & SURFACE QUALITY

Technical Characteristics	Industry Standards	Requirement	Actual Value
Length & width	BS EN ISO 10545-2	± 0.60% (max. ± 2.0mm)	Conforms
Thickness	BS EN ISO 10545-2	± 5% (max. ± 0.5mm)	Conforms
Edge straightness	BS EN ISO 10545-2	± 0.50% (max. ± 1.5mm)	Conforms
Orthogonality (squareness)	BS EN ISO 10545-2	± 0.50% (max. ± 2.0mm)	Conforms
Planarity (flatness)	BS EN ISO 10545-2	± 0.50% (max. ± 2.0mm)	Conforms
Appearance	BS EN ISO 10545-2	> 95%	Conforms

PRODUCT QUALITY & DURABILITY

Technical Characteristics	Industry Standards	Requirement	Actual Value
Water absorption	BS EN ISO 10545-3	≤ 0.5%	0.1% (Typical Value)
Modulus of rupture (bending strength)	BS EN ISO 10545-4	≥ 35 N/mm ²	Conforms
Breaking strength	BS EN ISO 10545-4	≥ 7.5mm ≥ 1300 N	Conforms
Linear thermal expansion coefficient	BS EN ISO 10545-8	Declared value	< 6.4*10 ⁻⁶ /°C-1 (Typical value)
Thermal shock resistance	BS EN ISO 10545-9	No visible defects	Resistant
Crazing resistance	BS EN ISO 10545-11	No visible signs	Conforms
Frost resistance	BS EN ISO 10545-12	No surface alteration	Resistant
Chemical resistance: Domestic chemicals & additives for swimming pools	BS EN ISO 10545-13	UB/GB min.	Conforms
Stain resistance	BS EN ISO 10545-14	Min. Class 3 – glazed	Conforms
Reaction to fire	Based on the decision 96/603/EC and its changes	A1 _{F,L} /A1	A1 _{F,L} /A1

