Mattone

Porcelain Design

Wall: DEBL 01 Segures Décor Matt

4 Colours / **1** Finish / **1** Size / **2** Décors

Mattone is a range of porcelain tiles inspired by flames, imparting distinctive character to its surfaces and creating textures and colours that convey authenticity and a weathered appearance. This ensemble proficiently blends darker and reddish tones, offering a rich chromatic palette that instils warmth and depth.

Floor: DEBL 02 Matt

Floor: DEBL 03 Matt

Wall: DEBL 04 Libori Décor Matt & DEBL 04 Matt
Floor: DEBL 04 Matt

DEBL 01

DEBL 02

DEBL 03

DEBL 04

Sizes

1

	Size (mm)	Thickness	Finish	Colour Availability
1	231 x 115 (N)	8.5	Matt	All colours

(N) Nominal size – pressed edge. Swatch colours may vary from original. Samples should be requested. Décors shown on next page.

V3 – High
Shade Variation

DOMUS

service@domusgroup.com | t: 020 8481 9500 | domusgroup.com

Décors

Libori Décor

DEBL 01

DEBL 02

DEBL 03



DEBL 04

Segures Décor

DEBL 01

DEBL 02

DEBL 03



DEBL 04

	Size (mm)	Thickness	Finish	Colour Availability
1	Libori Décor 231 x 115 (N)	8.5	Matt	All colours
	Segures Décor 231 x 115 (N)	8.5	Matt	All colours

(N) Nominal size – pressed edge. Swatch colours may vary from original. Samples should be requested.

V3 – High
Shade Variation

DOMUS

service@domusgroup.com | t: 020 8481 9500 | domusgroup.com

V3 – High Shade Variation

DEBL 01 Libori Décor

DEBL 03 Segures Décor

DEBL 01

DEBL 02

DEBL 03

DEBL 04

Mattone

Technical Data

Use: Floors & Walls
Product Code: DEBL

DIMENSION & SURFACE QUALITY

Technical Characteristics	Industry Standards	Requirement (for nominal size *N*) 70mm ≤N<150mmN ≥ 150mm		Actual Value
Length & width	BS EN ISO 10545-2	± 0.9mm	± 0.60% (max. ± 2.0mm)	Conforms
Thickness	BS EN ISO 10545-2	± 0.5mm	± 5% (max. ± 0.5mm)	Conforms
Planarity (flatness)	BS EN ISO 10545-2	± 0.75mm	± 0.50% (max. ± 2.0mm)	Conforms
Orthogonality (squareness)	BS EN ISO 10545-2	± 0.75mm	± 0.50% (max. ± 2.0mm)	Conforms
Appearance	BS EN ISO 10545-2	> 95%		Conforms

SLIP RESISTANCE

Technical Characteristics	Industry Standards	Requirement	Finish
Areas with footwear	BS EN 16165 Annex B	R11 from 19° to 27°	Matt
Areas with bare feet	BS EN 16165 Annex A	B over 18° to 24°	Matt
Slip resistance (Pendulum) Coefficient of friction	BS EN 16165	Test results upon request	

PRODUCT QUALITY & DURABILITY

Technical Characteristics	Industry Standards	Requirement	Actual Value
Water absorption	BS EN ISO 10545-3	≤ 0.5%	Conforms
Modulus of rupture (bending strength)	BS EN ISO 10545-4	≥ 35 N/mm²	Conforms
Breaking strength	BS EN ISO 10545-4	≥ 7.5mm ≥ 1300 N	Conforms
Resistance to surface abrasion (glazed tiles)	BS EN ISO 10545-7	PEI *see classifications below	Class 3
Thermal shock resistance	BS EN ISO 10545-9	No visible defects	Resistant
Crazing resistance	BS EN ISO 10545-11	No visible signs	Resistant
Frost resistance	BS EN ISO 10545-12	No surface alteration	Resistant
Chemical resistance: Low concentrations of acids & alkalis	BS EN ISO 10545-13	No visible defects	GLA
Domestic chemicals & additives for swimming pools	BS EN ISO 10545-13	UB/GB min.	GA
Stain resistance	BS EN ISO 10545-14	Min. Class 3 – glazed	Class 5
Reaction to fire	Based on the decision 96/603/EC and its changes	$A1_{FL}$/A1	$A1_{FL}$/A1
Recycled content			61%

***PEI classifications**
PEI 1 – Very light traffic
PEI 2 - Light traffic
PEI 3 - Light to moderate traffic
PEI 4 - Moderate to heavy traffic
PEI 5 - Heavy to extra heavy traffic

All test results are based upon current test data provided by the manufacturer and are provided in good faith. Domus Group cannot be held responsible for any variation in the test data due to changes in manufacture or material characteristics. Errors & omissions excepted. Please refer to Domus Group Terms & Conditions of Sale.
September 2026

DOMUS
service@domusgroup.com | t: 020 8481 9500 | domusgroup.com