

Essential Mood Magnum

Lightweight Slabs / Porcelain Concrete



9 Colours / 1 Finish / 4 Sizes / 2 Décors

Essential Mood Magnum presents a blend of earthy tones evocative of an easy-going lifestyle that embraces sustainability and a more mindful approach to interior design. This lightweight porcelain slab range is part of Florim's 'CarbonZero' selection of Climate-Positive surfaces, which reduce CO₂ in the atmosphere.





Wall: DMAG 264 Lined Décor Matt



Wall (right) & Floor: DMAG 263 Matt
Wall (centre): DMAG Dots Décor Matt


Sizes




DMAG 257




DMAG 258



DMAG 259




DMAG 260




DMAG 261




DMAG 262




DMAG 263



DMAG 264




DMAG 265




	Size (mm)	Thickness	Finish	Colour Availability
1	2797 x 1197 (R)	6	Matt	All colours
2	2397 x 1197 (R)	6	Matt	All colours
3	1197 x 1197 (R)	6	Matt	All colours
4	1197 x 597 (R)	6	Matt	All colours

(R) Rectified size - square edge with bevel. Décors and special pieces shown on next page. Swatch colours may vary from original. Samples should be requested.

Décors



DMAG 257 Lined Décor




DMAG 260 Lined Décor




DMAG 258 Lined Décor



DMAG 261 Lined Décor



DMAG 259 Lined Décor




DMAG 262 Lined Décor




DMAG 263 Lined Décor




DMAG 264 Lined Décor



DMAG 265 Lined Décor




DMAG Dots Décor



	Size (mm)	Thickness	Finish	Colour Availability
1	Lined Décor 2797 x 1197 (R)	6	Matt	All colours
2	Dots Décor 2797 x 1197 (R)	6	Matt	As shown

(R) Rectified size - square edge with bevel. Swatch colours may vary from original. Samples should be requested.




DOMUS

service@domusgroup.com | t: 020 8481 9500 | domusgroup.com


V2 - Moderate Shade Variation




DMAG 257




DMAG 258




DMAG 259




DMAG 260




DMAG 261



DMAG 262



DMAG 263



DMAG 264



DMAG 265

Essential Mood Magnum

Technical Data

Product Type: Unglazed Porcelain (BS EN 14411 - Group BIa)
Use: Floors & Walls
Product Code: DMAG

DIMENSION & SURFACE QUALITY

Technical Characteristics	Industry Standards	Requirement	Actual Value
Length & width	BS EN ISO 10545-2	± 0.60% (max. ± 2.0mm)	Conforms
Thickness	BS EN ISO 10545-2	± 5% (max. ± 0.5mm)	Conforms
Edge straightness	BS EN ISO 10545-2	± 0.50% (max. ± 1.5mm)	Conforms
Orthogonality (squareness)	BS EN ISO 10545-2	± 0.50% (max. ± 2.0mm)	Conforms
Planarity (flatness)	BS EN ISO 10545-2	± 0.50% (max. ± 2.0mm)	Conforms
Appearance	BS EN ISO 10545-2	> 95%	Conforms

SLIP RESISTANCE

Technical Characteristics	Industry Standards	Requirement	Finish
Areas with footwear	BS EN 16165 (Annex B)	R10 from 10° to 19°	Matt
Areas with bare feet	BS EN 16165 (Annex A)	B over 18° to 24°	Matt
Slip resistance (Pendulum) Coefficient of friction	BS EN 16165 (Annex C)	Test results upon request	

YPRODUCT QUALITY & DURABILITY

Technical Characteristics	Industry Standards	Requirement	Actual Value
Water absorption	BS EN ISO 10545-3	≤ 0.5%	0.08% (Typical value)
Modulus of rupture (bending strength)	BS EN ISO 10545-4	≥ 35 N/mm²	52 N/mm² (Typical value)
Breaking strength	BS EN ISO 10545-4	< 7.5mm ≥ 700 N	1350 N (Typical value)
Resistance to deep abrasion (unglazed tiles)	BS EN ISO 10545-6	≤ 175 mm³	140 mm³ (Typical value)
Thermal shock resistance	BS EN ISO 10545-9	No visible defects	Resistant
Frost resistance	BS EN ISO 10545-12	No surface alteration	Resistant
Chemical resistance: Low concentrations of acids & alkalis	BS EN ISO 10545-13	No visible defects	ULA
Domestic chemicals & additives for swimming pools	BS EN ISO 10545-13	UB/GB min.	UA
Stain resistance	BS EN ISO 10545-14	Declared value - unglazed	Class 4-5
Reaction to fire	Based on the decision 96/603/EC and its changes	A1 _{FL} /A1	A1 _{FL} /A1
Recycled content			5.8% - DMAG 257 11% - DMAG 258 - 265



All test results are based upon current test data provided by the manufacturer and are provided in good faith. Domus Group cannot be held responsible for any variation in the test data due to changes in manufacture or material characteristics. Errors & omissions excepted. Please refer to Domus Group Terms & Conditions of Sale. September 2024