Gubi Wall Slim

Lightweight Slabs / Ceramic Design





4 Colours / 1 Finish / 2 Sizes

Gubi Wall Slim is a highly versatile lightweight ceramic slab range for walls that utilises the ground-breaking Ductile^{*} technology. Due to the high adaptability of the large-sized sheets, it is perfect for interior cladding. Easy to handle thanks to its 6mm thickness.

Wall: DLGWS 02 Natural Floor: Gubi DLGF 02 Natural



DLGWS 01




DLGWS 02



DLGWS 03








| | Size (mm) | Thickness | Finish | Colour Availability |
|---|----------------|-----------|---------|---------------------|
| 1 | 2698 x 898 (R) | 6 | Natural | DLGWS 02, 03 & 04 |
| 2 | 1198 x 598 (R) | 6 | Natural | All colours |


(R) Rectified size - squared edge with bevel. For use on internal walls only. Swatch colours may vary from original. Samples should be requested.








DLGWS 01




2698mm



DLGWS 03

898mm



2698mm



Gubi Wall Slim

Technical Data

Product Type: Glazed Ceramic (BS EN 14411 – Group BIII)

Use: Walls (Internal only)

Product Code: DLGWS

DIMENSION & SURFACE QUALITY

| Technical Characteristics | Industry Standards | Requirement | Actual Value |
|---|--------------------|---|--------------|
| Length & width | BS EN ISO 10545-2 | ± 0.50% (max. ± 2.0mm) | Conforms |
| Thickness | BS EN ISO 10545-2 | ± 10% (max. ± 0.5mm) | Conforms |
| Planarity (flatness): Centre curvature | BS EN ISO 10545-2 | + 0.5% (max. + 2.0mm - 0.3% (max 1.5mm) | Conforms |
| Edge curvature | BS EN ISO 10545-2 | + 0.5% (max. + 2.0mm) - 0.3% (max 1.5mm) | Conforms |
| Warpage | BS EN ISO 10545-2 | ± 0.5% (max. ± 2.0mm) | Conforms |
| Appearance | BS EN ISO 10545-2 | > 95% | Conforms |

| Technical Characteristics | Industry Standards | Requirement | Actual Value |
|---|---|--|----------------------------|
| Water absorption | BS EN ISO 10545-3 | > 10% | > 10% (typical value) |
| Modulus of rupture (bending strength) | BS EN ISO 10545-4 | < 7.5mm thick \ge 15 N/mm ² | > 20 N/mm² (typical value) |
| Breaking strength | BS EN ISO 10545-4 | $<~7.5mm$ thick ≥ 200 N | > 400 N (typical value) |
| Crazing resistance | BS EN ISO 10545-11 | No visible defects | Resistant |
| Chemical resistance: Low concentrations of acids & alkalis | BS EN ISO 10545-13 | No visible defects | GLA |
| Domestic chemicals & additives for swimming pools | BS EN ISO 10545-13 | GB min. | GA |
| Stain resistance | BS EN ISO 10545-14 | Min. Class 3 | Class 5 |
| Reaction to fire | Based on the decision 96/603/EC and its changes | Α1 | A1 |
| Recycled content | | | 30% |

PRODUCT QUALITY & DURABILITY



All test results are based upon current test data provided by the manufacturer and are provided in good faith. Domus Group cannot be held responsible for any variation in the test data due to changes in manufacture or material characteristics. Errors & omissions excepted. Please refer to Domus Group Terms & Conditions of Sale